

This report is a reissue of, but not a replacement for Report No 16101.22. This version incorporates an alternative name used for the same product, at request of client.



Accredited for compliance with ISO/IEC 17025 – Testing
 NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports
 Accreditation No. 2735

DRY FLOOR FRICTION SLIP RESISTANCE TEST

Dulux Avista General Purpose Sealer Matt with Crushed Glass applied to steel trowel finish concrete

Prepared for: Parchem Construction Supplies Pty Ltd
 ATTENTION: Peter Battista
 7 Lucca Road
 WYONG NSW 2259

Specimen Description: Dulux Avista General Purpose Sealer Matt with Crushed Glass applied to steel trowel finish concrete, 450x450mm.

No. of Specimens: 1 off (Sampling conducted by client).

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Test Condition & Slope: Unfixed. Slope - Not Applicable

Test Direction: Test direction not applicable.

Air Temperature: 22°C

Test Standard: AS 4586: 2013 Slip resistance classification of new pedestrian surface materials, Appendix B - Dry Floor Friction Test.

Test Location: ATTAR, 44-48 Rocco Drive, Scoresby, VIC.

Test Date: 14 September 2021

Test Equipment: Tortus Floor Friction Tester Mk II, Serial Number 233.

Slider Rubber: Slider 96 Batch #4 prepared on P400.

Test Personnel: Trent Considine

Run:	1	2
Coefficient of Friction (COF):	0.46	0.42
Mean COF (rounded to 0.05):	0.45	
Classification:	D1	


These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

Prepared by:



Daniel King BSc/BEng (Mat) Hons., MIEAust
 General Manager – Compliance Services
 Approved Signatory

Reviewed by:



Marcus Braché
 Senior Engineering Technician
 Approved Signatory




Figure 1: Dulux Avista General Purpose Sealer Matt with Crushed Glass applied to steel trowel finish concrete.



CLASSIFICATION CRITERIA – AS 4586: 2013
Dry Floor Friction Test - Appendix B

Slip resistance

The 'dry floor friction' test method in Appendix B is not suitable for heavily profiled surfaces or carpets.

Compliance

The surface shall comply with the stated classification for the test method that is nominated and declared by the manufacturer or supplier.

**TABLE 3: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS
ACCORDING TO THE AS 4586 DRY FLOOR FRICTION TEST**

Classification	Floor friction tester mean value
D1	≥ 0.40
D0	< 0.40

Means of demonstrating compliance

Pedestrian surfaces that are classified in accordance with Table 3 where appropriate, shall meet the following criteria:

- (a) The mean test results shall be as follows:
- (i) For Classification D1 in Table 3—
 - (A) the mean of the test results shall be equal to or greater than 0.4; and
 - (B) each individual slope corrected result shall be equal to or greater than 0.35.
- If either of these criteria is not met, the lot shall be considered to be Classification D0.
- (b) The classification in accordance with Table 3 shall be determined by—
- (i) selecting and testing specimens at random as specified in Appendix B of AS4586; or
 - (ii) carrying out continuous testing and process control in accordance with AS 3942.
- (c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to—
- (i) disregard the first sample, resample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or
 - (ii) subdivide the lot into smaller lots of different quality, resample, retest and reclassify each of the smaller lots.