

# Dulux Avista Resurfacing Coloured Compound



## Spray or trowel applied decorative concrete for application over existing concrete surfaces

### Description

Dulux Avista Resurfacing Coloured Compound is a decorative concrete coating, suitable for application over existing cured concrete surfaces.

Dulux Avista Resurfacing Coloured compound is made up of two components. Dulux Avista Resurfacing Coloured Compound and clean potable water.

A range of colours are available. See colour chart for further details.

### Uses

The Dulux Avista System is based on a blend of dry powders, polymers and graded aggregates. It is a suitable application for driveways, patios, pool surrounds, house and commercial decorative floors and certain road applications.

### Advantages

- Extended working life for applications above 30°C.
- Improved flow properties for ease of spray application.
- Excellent durability.
- Excellent adhesion to most concrete substrates.
- Water based providing convenient water clean up.
- Anti-slip finishes obtainable.
- Wide range of colours and the ability to create a variety of finishes.

### Properties

The following results were obtained at a water / powder ratio of 0.18 and a temperature of 23°C

<b>Compressive Strength</b> (AS1478.2-2005)	10 MPa @ 1 day 30 MPa @ 7 days 40 MPa @ 28 days
<b>Modulus of Rupture</b> (Flexural Strength) (AS1012.11-2000)	5 MPa @ 1 day 7 MPa @ 7 days 10 MPa @ 28 days
<b>Indirect Tensile Strength</b> (AS1012.10-2000)	1 MPa @ 1 day 3 MPa @ 7 days 5 MPa @ 28 days
<b>Taber Abrasion Index</b> (CS10 Wheel, 1kg load, 1000 cycles)	< 100

Slip Resistance Classification AS 4586-2013

Type of application	Wet Pendulum	Dry Friction
Smooth Trowel	P1	D1
Spray	P5	D1

NOTE: Both tested samples were coated with two coats of Avista General Purpose Sealer. The slip rating is texture dependent.

### Application Instructions

#### Preparation

Preparation of the area is extremely important to ensure good adhesion.

Ensure concrete is sufficiently cured (recommended minimum 14 days).

If surface contains cracks, repair or filling should be undertaken, however, future movement in the concrete may cause cracks to appear that may affect adhesion and could result in chipping of the Dulux Avista Resurfacing Coloured Compound coating.

- Concrete is to be clean and free of grease, oil, paint or any curing agent. Stiff broom and general purpose cleaner recommended.
- Pressure clean surface at minimum 2000 psi and allow to dry.
- Acid etch with hydrochloric acid. Dilute approx 20 parts water to 1 part acid (depending on porosity) to remove any loosely bound cement and laitance.  
**NOTE:** smooth concrete will require a higher acid content. Maximum strength - 10 parts water to 1 part acid.
- Pressure clean immediately to clean and remove all remnants of acid (do not allow acid to dry on surface). Pressure clean at minimum 2000 psi.

#### Masking and taping

- Ensure all surfaces surrounding the area to be sprayed, including grass and plants, should be covered or masked and taped.
- Expansion joints should be taped with filament tape, and removed after final spray.

#### Priming

- The area is then primed with Dulux Avista Resurfacing Primer.  
1 part Dulux Avista Resurfacing Primer : 3 parts water by volume.
- Smooth trowelled floors require a mix ratio of 1 part Dulux Avista Resurfacing Primer : 4 parts water by volume.
- Apply evenly on surface by broom, roller or sprayer.
- Do not allow primer to pool. If primer pools, spread across surface with a broom. Allowing primer to dry in a pooling area can affect adhesion.

# Dulux Avista Resurfacing Coloured Compound

---

## Mixing

- Mixing requires a clean, 20L bucket.
- Add required amount of clean potable water (3.5 - 3.85L max).
- Slowly add Dulux Avista Resurfacing Coloured Compound, mixing continually.
- Once full content has been added, mix for a further 3 minutes. This step is critical in activating the polymers to achieve an even consistent mixture.
- Ensure not to create an excessive vortex or aerate too much, creating air bubbles in the mix, as this can cause delamination and a weak surface.

## Spray application

- Application will require a moisture trap air compressor (minimum 15 cfm) with a 20m hose and an appropriate hopper gun.
- Add mix to hopper, ensuring not to overfill - recommend half full.
- Before applying to surface, spray on separate fibro test board to obtain desired texture. Adjust pressure to vary texture.
- Spray evenly across surface in a circular motion, holding the hopper approximately 600mm from the ground.
- Once area has been completely covered, allow to dry sufficiently to walk on.
- Repeat application as above. Minimum 2 spray coats required to achieve sufficient wear factor.

## Trowel application

- Pour a manageable quantity of Dulux Avista mixture onto the primed concrete surface and squeegee or trowel evenly over the surface.
- Do not exceed a thickness of 4 mm per coat, as this may lead to shrinkage cracking.
- Subsequent trowel coats can be applied to achieve special decorative finishes.

## Special decorative finishes - training course

Application of special decorative finishes, including:

- Design trowel down,
- Stone finish,
- Woodgrain
- Fleck finish,
- Multi-coloured spraying,
- Stencil and tape finishes,

Please contact your Dulux Avista Account Manager for training course information.

## Sealing

- The Dulux Avista Resurfacing System can be sealed once the surface is completely dry, refer to Dry Test.
- Can be sealed using Dulux Avista General Purpose Semi Gloss, General Purpose Matt, Extended Wear or 2 Pack Urethane Sealer.
- Refer to relevant Dulux Avista Sealer Technical Data Sheet. Note: Not to be sealed with Dulux Avista Exposed Aggregate Sealer, Waterbased Sealer or Sealer Primer.

## Dry Test

- Place a piece of plastic over a small area, tape the edges and leave for 1 hour.
- Remove plastic, if there is no moisture on either surface, concrete is sufficiently dry for sealing.

## Sealer Curing Time

After sealing it is recommended that the sealed surface be protected from:

- Rain/water/sprinkler systems for minimum 6 hours
- Foot traffic for a minimum of 24 hours
- Vehicle traffic for a minimum of 5 days

The time depends on weather conditions and coating thickness, therefore, check suitability before allowing traffic.

## Limitations

- Do not apply in temperatures below 10°C as curing time is significantly delayed. It is not advisable to apply onto very hot surfaces (greater than 40°C) as this can affect cure. Therefore, under very hot conditions it is advisable to shade the application area.
- Dulux Avista Resurfacing Coloured Compound coating is a decorative coating and cracks in the concrete base may reflect through the surface.

# Dulux Avista Resurfacing Coloured Compound

---

## Supply

<b>FD500819-20KG</b>	AVS RESURFACING COMPOUND CHARCOAL 20KG
<b>FD500820-20KG</b>	AVS RESURFACING COMPOUND BLUESTONE 20KG
<b>FD500815-20KG</b>	AVS RESURFACING COMPOUND SANDYBEIGE 20KG
<b>FD500816-20KG</b>	AVS RESURFACING COMP DARK TERRACTTA 20KG
<b>FD500817-20KG</b>	AVS RESURFACING COMPOUND DESERTSAND 20KG
<b>FD500818-20KG</b>	AVS RESURFACING COMPOUND WHITE 20KG
<b>FD500821-20KG</b>	AVS RESURFACING COMP FRENCH GREY 20KG
<b>FD500897-20KG</b>	AVS RESURFACING COMP GUNMETAL 20KG

## Coverage & Yield

20 kg bag yields 12.5-13 litres.

20 kg bag covers approximately 20-24 m<sup>2</sup> per coat.

Minimum 2 coats required.

## Shelf Life

12 months if kept unopened and stored in cool, dry conditions. After this time, product should be checked to ensure its suitability for use.

### Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Dulux Avista website [www.duluxavista.com.au](http://www.duluxavista.com.au). Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In an emergency, contact any Poisons Information Centre (Telephone 131 126 within Australia) or a doctor for advice.

### Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Dulux Avista does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



**Dulux Avista**  
1956 Dandenong Road, Clayton VIC 3168  
Telephone: 1800 801 108  
ABN 80 069 961 968

Distributed in New Zealand by: Concrete Plus Limited  
150 Hutt Park Road, Gracefield Ph: 0800 657 156